


# DM-7001



## Double Coated Polyester Film

#### **CONTENTS**

Face	0.5 mil polyester
Adhesive	Medical grade, pressure-sensitive acrylic
Backing	Poly coated two-side/silicone coated two-side, 75 lb basis weight

## **FACE PROPERTIES**

## Test method

Thickness	0.5 mil	
Tensile Strength	3200 psi	ASTM D-882
Elongation	100%	ASTM D-882

Typical substrate values of uncoated materials.

#### **ADHESIVE PROPERTIES**

#### Test method

Peel Adhesion	>60 oz/in	PSTC-3
Polyken Probe Tack	300 g/in²	ASTM D-2979
Loop Tack	1650 g/in²	PSTC-16
Thickness	1.4 mil Side: exposed liner	
	Cytotoxicity	Pass
Biocompatibility	Primary Dermal	Pass
	Buehler	Pass

Product safety sheets are contained on file.

## PRODUCT DESCRIPTION

DM-7001 is a clear polyester film. It is coated on both sides with a medical grade acrylic adhesive and supplied on a paper liner.

#### SPLICES

Splices on tape and liner are functional in that they are intended for continuous process conditions.

Materials will have core labeling stating the part number, roll number, lot number, width, and linear feet per roll. Note: Any additional labeling requirements should be noted at time of order entry.

STANDARD LABELING

Materials will have core labeling somewher, roll number, lot number feet per roll. Note: Any additional is should be noted at time of order ending the should be noted at time of order ending the should be noted at time of order ending the should be noted at time of order ending the should be noted at time of order ending the should be noted in original packaging at temperatures between the should be stored in original packaging at temperatures between the should be should be should be stored in original packaging at temperatures between the should be Material traceability must comply with current Good Manufacturing Practices. Each shipment of material will contain a lot number, which is traceable through production records. Certificate of Conformance will

Product should be stored in original protective packaging at temperatures between 50-80°F.

**ROLL DIMENSIONS** Smaller roll length by request.