

DM-7210



Single Coated Polypropylene Film

CONTENTS

Face	1 mil polypropylene film	
Adhesive Medical grade, pressure-sensitive acrylic		
Backing	Silicone coated one-side, 54 lb basis weight	

FACE PROPERTIES

Test method

Thickness	1 mil	
Tensile Strength	MD 10000 psi CD 22000 psi	ASTM D-882
Elongation	MD 120% CD 50%	ASTM D-882

Typical substrate values of uncoated materials.

ADHESIVE PROPERTIES

Test method

Peel Adhesion	>900 g/in	PSTC-1
Polyken Probe Tack	580 g/in²	ASTM D-2979
Loop Tack	1380 g/in²	PSTC-16
Thickness	1.4 mil	
Biocompatibility	Cytotoxicity Primary Dermal Buehler	Pass Pass Pass

Adhesive testing generated from a 2 mil PET lab standard. Product safety data sheets are contained on file.

PRODUCT DESCRIPTION

DM-7210 is a white, pearlized OPP (oriented polypropylene) film. It is coated on one side with a medical grade acrylic adhesive and supplied on a paper liner.

Splices on tape and liner are functional in that they are intended for continuous process conditions.

STANDARD LABELING

Materials will have core labeling stating the part number, roll number, lot number, width, and linear feet per roll. Note: Any additional labeling requirements should be noted at time of order entry.

TRACEABILITY

Material traceability must comply with current Good Manufacturing Practices. Each shipment of material will contain a lot number, which is traceable through production records. Certificate of Conformance will accompany each shipment.

STORAGE CONDITIONS

Product should be stored in original packaging at temperatures between the stored in original packaging at temperatures between the stored in original packaging at temperatures between the stored in original packaging at temperature should be stored in original packaging at temperatures between the stored in original packaging at the stored in Product should be stored in original protective packaging at temperatures between 50-80°F.

ROLL DIMENSIONS Smaller roll length by request.